SITEDRAIN™ STRIP 9800

PREFABRICATED STRIP DRAIN





PRODUCT OVERVIEW

SITEDRAIN Strip 9800 geocomposite strip drain products are composed of a dimpled polymeric perforated core fully wrapped in a nonwoven geotextile. The geotextile allows water to pass through while retaining backfill materials. The perforated core allows water collection from all sides and provides a continuous flow path to designated drainage exits.

SITEDRAIN Strip 9800 products provide a value engineered alternative to perforated pipe and aggregate subsurface drainage systems requiring high strength, high flow capacity, and a geotextile meeting AASHTO M288 Class 1 subsurface drainage requirements.

PROPERTY 1	TEST METHOD	UNIT OF MEASURE	Typical Value	MARV
GEOTEXTILE				1
Material ²			PP, NPNW	PP, NPNW
Survivability	AASHTO M288	Class	1	1
Grab Tensile Strength	ASTM D4632	lbs	245	205
		N	1,090	912
Grab Elongation	ASTM D4632	%	60	50
CBR Puncture	ASTM D6241	lbs	580	535
		N	2,580	2,380
Trapezoidal Tear	ASTM D4533	lbs	100	80
		N	445	356
UV Resistance	ASTM D4355	% / 500 Hrs	70	70
Apparent Opening Size (AOS) ³	ASTM D4751	sieve	80	80
		mm	0.180	0.180
Permittivity	ASTM D4491	sec ⁻¹	1.8	1.4
Water Flow Rate	ASTM D4491	gpm / ft²	135	100
		Lpm / m ²	5,501	4,074
CORE				
Compressive Strength	ASTM D6364	psf	9,500	-
	ASTM D1621	kPa	455	-
Thickness	ASTM D5199	in	1.0	-
		mm	25.4	-
In-Plane Flow Rate 4	ASTM D4716	gpm/ft	21	-
		Lpm/m	261	-

MODEL	WIDTH	ROLL Length	ROLL WEIGHT	ITEM CODE
9806	6"	150′	34 lbs	10700
9812	12"	150′	60 lbs	10710
9812	12"	500′	200 lbs	14390
9818	18"	150′	78 lbs	10720
9824	24"	150′	104 lbs	10730
9836	36"	100′	104 lbs	10740

All technical information contained in this document is accurate as of publication. AWD reserves the right to make changes to products and literature without notice. Please refer to our website for the most current technical information available.

WEB: awd-usa.com

Unless otherwise noted, all physical and performance properties listed are Typical Value or Minimum Average Roll Value (MARV) as defined in ASTM D4439.

² PP = Polypropylene; NPNW = Needle-Punched Nonwoven; WM = Woven Monofilament; SBNW = Spunbonded Nonwoven

³ Values for AOS represent Maximum Average Roll Value (MaxARV).

⁴ In-plane flow rate measured at 3,600 psf (172 kPa) compressive load and a hydraulic gradient of 0.1.